

产品名称 Product Name	索引号 C.I No.	色卡 Color Shade		技术指标 Technical Data									应用范围 Range of Applications						
		原色 Full Shade	冲淡色 Reduction	PH值 PH Value	吸光度 Optical Density m/100g	牢度 Fastness 1-8	耐热性 Heat Resistance ℃	耐水性 Water Resistance 1-5	耐皂性 Oil Resistance 1-5	耐酸性 Acid Resistance 1-5	耐碱性 Alkali Resistance 1-5	分散染料 Disperse Dyes	溶剂型染料 Solvent-based Inks	水性染料 Water-based Inks	工业染料 Industry Dye	粉末染料 Powder Dye	水性涂料 Water-based Coating	纺织印花 Textile Printing	塑料 Plastic
耐晒黄 Fast Yellow G	P.Y1			6-8	≤40	7	160	4	4	5	5	☆		★	★		★	★	
耐晒黄 Fast Yellow 10G	P.Y3			6-8	≤40	7	160	4	5	5	5	☆		★	★		★	★	
联苯胺黄 Benzidine Yellow G	P.Y12			6-8	≤50	5-6	200	5	5	5	5	★	★	★	★	☆	★	★	★
联苯胺黄 Benzidine Yellow GB	P.Y12			6-8	≤50	5-6	200	5	5	5	5	★		☆				☆	★
联苯胺黄 Benzidine Yellow DHG	P.Y12			6-8	≤50	5-6	180	5	5	5	5	★						☆	
联苯胺黄 Benzidine Yellow GS	P.Y12			6-8	≤45	5-6	180	5	5	5	5		★		☆	☆			
联苯胺黄 Benzidine Yellow GW	P.Y12			6-8	≤50	5-6	180	5	5	5	5			★			★	★	
永固黄 Permanent Yellow GR	P.Y13			6-8	≤45	6	220	5	4	5	5	★		☆	★	★	★	★	★
永固黄 Permanent Yellow GRS	P.Y13			6-8	≤45	6	200	5	4	5	5	☆	★						
永固黄 Permanent Yellow GRW	P.Y13			6-8	≤45	6	200	5	4	5	5			★			★		
永固黄 Permanent Yellow 2GS	P.Y14			6-8	≤45	6	220	5	4	5	5	★	☆	★	☆	☆	★	★	★
永固黄 Permanent Yellow 14S	P.Y14			6-8	≤45	6	180	5	4	5	5		★						
永固黄 Permanent Yellow 2GW	P.Y14			6-8	≤45	6	180	5	4	5	5			★			★	★	
永固黄 Permanent Yellow 2G	P.Y17			6-8	≤45	6	220	5	4	5	5	★	☆	☆	★	☆			★
颜料黄 Pigment Yellow WSR	P.Y62			6-8	≤55	7	260	5	5	5	5								★
永固黄 Permanent Yellow RN	P.Y65			6-8	≤45	6	180	5	4	5	5				★	★	☆		
耐晒艳黄 Brilliant Yellow 5GX	P.Y74			6-8	≤45	6-7	180	5	4	5	5	☆		★	☆		★	☆	
耐晒艳黄 Brilliant Yellow 5GS	P.Y74			6-8	≤45	6-7	180	5	4	5	5	☆	★	☆					
联苯胺黄 Benzidine Yellow 10G	P.Y81			6-8	≤55	7	240	5	4	5	5	☆		★	☆			☆	★
永固黄 Permanent Yellow HR-A	P.Y83			6-8	≤45	7	220	5	5	5	5	☆		★	☆	☆	★	★	☆
永固黄 Permanent Yellow HR-B	P.Y83			6-8	≤45	7	220	5	5	5	5				★	★			★
永固黄 Permanent Yellow HRS	P.Y83			6-8	≤45	7	200	5	5	5	5		★		☆				
永固黄 Permanent Yellow FGL	P.Y97			6-8	≤45	7	240	5	4	5	5	☆	☆	☆	★	★	☆	☆	★

产品名称 Product Name		索引号 C.I No.	色卡 Color Shade		技术指标 Technical Data								应用范围 Range of Applications							
			原色 Full Shade	冲淡色 Reduction	PH值 PH Value	吸油量 Oil Absorption ml/100g	耐光性 Light Fastness 1-8	耐热性 Heat Resistance °C	耐水性 Water Resistance 1-5	耐碱性 Oil Resistance 1-5	耐酸性 Acid Resistance 1-5	耐盐性 Alkal Resistance 1-5	油墨类 Offset Inks	溶剂类 Solvent-based Inks	水性类 Water-based Inks	工业染料 Industry Paint	粉末类 Powder Paint	水性涂料 Water-based Coating	纺织印染 Textile Finishing	塑料 Plastic
永固黄	Permanent Yellow 110	P.Y110			6-8	≤55	8	300	5	5	5	5	☆	☆	☆	★	★	★	★	★
永固黄	Permanent Yellow 138	P.Y138			6-8	≤55	8	300	5	5	5	5	☆	☆	☆	★	★	★	☆	★
耐晒黄	Fast Yellow H4G	P.Y151			6-8	≤55	7-8	260	5	5	5	5	★	★	★	★	★	★	★	★
耐晒黄	Fast Yellow H3G	P.Y154			6-8	≤55	8	240	5	5	5	5	★	☆	★	★	★	★	★	★
耐晒黄	Fast Yellow 3GP	P.Y155			6-8	≤55	7-8	260	5	5	5	5	★	☆	★	★	★	★	★	★
永固黄	Permanent Yellow GRP	P.Y168			6-8	≤55	7-8	260	5	4	5	5						☆	★	
永固黄	Permanent Yellow HSF	P.Y174			6-8	≤50	5-6	220	4	5	5	5	★							★
耐晒黄	Fast Yellow HG	P.Y180			6-8	≤60	7-8	280	5	4-5	5	5	★	☆	★	★	★	★	☆	★
永固黄	Permanent Yellow H3R	P.Y181			6-8	≤60	7-8	300	5	5	5	5					★			★
永固黄	Permanent Yellow 3RP	P.Y183			6-8	≤50	8	300	5	5	5	5								★
永固黄	Permanent Yellow 2RP	P.Y191			6-8	≤50	7-8	280	5	5	5	5								★
永固桔黄	Fast Orange G	P.O13			6-8	≤50	6	180	4	5	5	4	☆	☆	★	★	☆	★	★	★
永固橙	Permanent Orange RL	P.O34			6-8	≤50	6	220	4	5	4	5	☆	★	★	★	☆	★	★	★
耐晒橙	Fast Orange HL	P.O36			6-8	≤60	7-8	260	5	5	5	5	★	☆	★	★	★	★	★	★
耐晒橙	Fast Orange GP	P.O64			6-8	≤60	7-8	280	5	5	5	5	★	☆	★	★	★	★	★	★
永固橙	Permanent Orange 73	P.O73			6-8	≤60	8	300	5	5	5	5	★	☆	★	★	★	★	★	★
永固大红	Fast Red F2R	P.R2			6-8	≤50	6	160	4	4	4	4			★	☆	☆	★	★	
甲苯胺红	Toluidine Red RN	P.R3			6-8	≤50	6-7	160	4	4	4	4				★	☆			
永固红	Permanent Red F4R	P.R8			6-8	≤55	5	160	4	4	4	5	☆	☆	★			★	★	
甲苯胺紫红	Toluidine Maroon	P.R13			6-8	≤50	5-6	160	4	4	4	4				★	☆	☆		
大红粉	Scarlet Red FR	P.R21			6-8	≤45	5-6	160	4	4	5	5	☆	☆	★	☆	★			
耐晒亮红	Fast Brilliant Red N	P.R22			6-8	≤55	5	160	4	3	3	3			★			★	★	
坚固玫红	Rose Red	P.R23			6-8	≤45	5	160	4	3	5	3	☆		★			★	★	

产品名称 Product Name		索引号 C.I No.	色卡 Color Shade		技术指标 Technical Data								应用范围 Range of Applications							
			原色 Full Shade	冲淡色 Reduction	PH值 PH Value	吸油量 Oil Absorption m <sup>2</sup> /100g	耐光性 Light Fastness 1-8	耐热性 Heat Resistance °C	耐水性 Water Resistance 1-5	耐油性 Oil Resistance 1-5	耐酸性 Acid Resistance 1-5	耐碱性 Alkal Resistance 1-5	溶剂油墨 Solvent-based Inks	水性油墨 Water-based Inks	工业染料 Industry Faint	粉末染料 Powder Faint	水性涂料 Water-based Coating	纺织印花 Textile Printing	塑料 Plastic	
耐晒大红	Fast Scarlet BBN	P.R48:1			7-8	≤50	6	220	4	4	4	5	☆			★		☆	★	
耐晒艳红	Fast Brilliant Red BBC	P.R48:2			7-8	≤50	6	200	4	4	4	5	☆			★	★			☆
耐晒艳红	Fast Brilliant Red BBC-S	P.R48:2			7-8	≤50	6	200	4	4	5	5	☆	★	☆	★				☆
耐晒艳红	Fast Brilliant Red 2BP	P.R48:2			7-8	≤55	6	250	5	5	4	5								★
耐晒大红	Fast Red BBS	P.R48:3			7-8	≤50	6	200	4	4	4	5	☆	☆	☆	★	★	☆		☆
耐晒大红	Fast Red H2BS	P.R48:3			7-8	≤55	6	250	5	5	4	5								★
耐晒深红	Fast Red BBM	P.R48:4			7-8	≤55	6-7	200	4	4	4	5	☆	☆	☆	★	★	☆	☆	★
立索尔大红	Lithol Scarlet R	P.R49:1			7-8	≤50	4	160	4	4	3	3	★		☆	☆				
立索尔大红	Lithol Scarlet R-W	P.R49:1			7-8	≤50	5	160	3	3	3	3			★			★		
金光红	Permanent Lake Red C	P.R53:1			7-9	≤50	5	200	5	5	4	4	★	☆	★	★	☆	☆		☆
金光红	Permanent Lake Red C-P	P.R53:1			7-9	≤45	5-6	240	5	5	4	4								★
金光红	Permanent Lake Red C-W	P.R53:1			7-9	≤50	5	200	5	5	3	3	☆		★			☆		
金光红	Permanent Lake Red C-S	P.R53:1			7-9	≤45	5	200	4	4	4	4	☆	★		★				☆
颜料宝红	Permanent Rubine BK	P.R57:1			7-8	≤55	5-6	200	4	4	4	4	★							☆
颜料宝红	Permanent Rubine BK-WB	P.R57:1			7-8	≤50	5-6	180	4	4	4	4	☆		★			★		
颜料宝红	Permanent Rubine BK-WY	P.R57:1			7-8	≤50	5-6	180	4	4	4	4	☆		★			★		
颜料宝红	Permanent Rubine L4B	P.R57:1			7-8	≤55	5-6	180	4	4	4	4	★			☆				☆
颜料宝红	Permanent Rubine L6B	P.R57:1			7-8	≤55	5-6	180	4	4	4	4	★			☆				☆
颜料宝红	Permanent Rubine 6B	P.R57:1			7-8	≤55	5-6	200	4	4	4	4	★			★				☆
颜料宝红	Permanent Rubine H4BL	P.R57:1			7-8	≤50	5-6	180	4	4	4	4	☆	★		★				☆
颜料宝红	Permanent Rubine H4GL	P.R57:1			7-8	≤55	5-6	180	4	4	4	4	☆	★		☆				
颜料宝红	Permanent Rubine 4BP	P.R57:1			7-8	≤55	6	250	4	4	4	4								★
颜料宝红	Lithol Bordeaux 2R	P.R63:1			7-8	≤50	5-6	180	4	4	4	4				★				★

产品名称 Product Name	索引号 C.I No.	色卡 Color Shade		技术指标 Technical Data								应用范围 Range of Applications							
		原色 Full Shade	冲淡色 Reduction	PH值 PH Value	吸油量 Oil Absorption ml/100g	耐光性 Light Fastness 1-8	耐热性 Heat Resistance °C	耐水性 Water Resistance 1-5	耐皂性 Oil Resistance 1-5	耐酸性 Acid Resistance 1-5	耐碱性 Alkali Resistance 1-5	分散染料 Disperse Dyes	溶剂型染料 Solvent-based Inks	水性油墨 Water-based Inks	工业染料 Industry Paint	粉末染料 Powder Paint	水性涂料 Water-based Coating	印花染料 Textile Printing	塑料 Plastic
桃红色原 Fast Pink Toner	P.R81			7-9	≤55	4	140	4	4	4	3	★		☆					
桃红色原 Fast Pink Toner W	P.R81			7-9	≤55	4	140	4	4	4	3	☆		★				☆	
桃红色原 Fast Pink Toner NC	P.R81			7-9	≤55	4	140	4	4	4	3		★						
桃红色淀 Fast Pink Lake G	P.R81			7-9	≤55	4	140	4	4	4	3	★	☆	☆					
永固红 Permanent Red FGR	P.R112			5-7	≤50	6	200	5	4	5	5			★	★	★	★	★	
永固红 Permanent Red 122	P.R122			6-8	≤55	8	300	5	5	5	5	★	☆	☆	★	★	★	★	★
永固桃红 Permanent Pink FBB	P.R146			6-8	≤50	5	180	5	4	4	4	☆	★	☆	★	☆	☆	★	
颜料红 Fast Red W	P.R169			7-8	≤55	4	140	4	4	3	3	☆		★					
永固红 Fast Red F2RK	P.R170			6-8	≤50	7-8	220	5	5	5	5	☆	★	★	★	★	★	☆	★
永固红 Fast Red F3RK	P.R170			6-8	≤50	7-8	220	5	5	5	5	☆	★	★	★	★	★	☆	★
永固红 Fast Red F5RK	P.R170			6-8	≤50	7-8	220	5	5	5	5	☆	★	★	★	★	★	★	★
耐晒红 Fast Red HFT	P.R175			6-8	≤90	7	280	5	5	5	5	☆	☆	☆	★	★	★	★	★
耐晒红 Fast Red HF3C	P.R176			6-8	≤90	7-8	260	5	5	5	5	★	☆	★	★	★	★	★	★
永固红 Permanent Red HF4C	P.R185			6-8	≤90	7-8	250	5	5	5	5	★	☆	★	★	★	★	★	★
耐晒红 Fast Red HF2B	P.R208			6-8	≤90	7-8	250	5	5	5	5	★	☆	★	★	★	★	★	★
DPP红 Pigment Red 254	P.R254			6-8	≤60	8	300	5	5	5	5	★	★	★	★	★	★	★	★
品蓝色原 Fast Blue Toner	P.B1			7-8	≤55	4	140	4	4	4	4	☆		☆					
品蓝色淀 Fast Blue Lake BO	P.B1			7-8	≤55	4	140	4	4	4	3	☆		☆					
酞青蓝 Phthalocyanine Blue B	P.B15:0			6-9	≤45	7	220	5	5	5	5	★		★	★	★	★	★	★
酞青蓝 Phthalocyanine Blue BW	P.B15:0			6-9	≤45	7	200	5	5	5	5	☆		★			☆	★	
酞青蓝 Phthalocyanine Blue BP	P.B15:0			6-9	≤45	7	240	5	5	5	5					☆			★
酞青蓝 Phthalocyanine Blue BS	P.B15:1			6-9	≤45	7	240	5	5	5	5	★	☆	★	★	★	★	★	★
酞青蓝 Phthalocyanine Blue BSW	P.B15:1			7-8	≤45	7-8	200	5	5	5	5	☆		★	☆		★	★	

产品名称 Product Name	索引号 C.I No.	色卡 Color Shade		技术指标 Technical Data								应用范围 Range of Applications							
		原色 Full Shade	冲淡色 Reduction	PH值 PH Value	吸油量 Oil Absorption ml/100g	遮盖力 Light Fastness 1-8	耐热性 Heat Resistance °C	耐水性 Water Resistance 1-5	耐溶剂 Oil Resistance 1-5	耐酸性 Acid Resistance 1-5	耐碱性 Alkal Resistance 1-5	耐晒性 Light Resistance	溶剂油墨 Solvent-based Inks	水性油墨 Water-based Inks	工业油墨 Industry Paint	粉末涂料 Powder Paint	水性涂料 Water-based Coating	印花涂料 Textile Printing	塑料 Plastic
酞青蓝 Phthalocyanine Blue BSP	P.B15:1			6-9	≦45	7	260	5	5	5	5					★			★
酞青蓝 Phthalocyanine Blue BN	P.B15:2			6-9	≦45	7	240	5	5	5	5	★			★	☆			☆
酞青蓝 Phthalocyanine Blue BNP	P.B15:2			6-9	≦45	7	240	5	5	5	5					★			★
酞青蓝 Phthalocyanine Blue BGS	P.B15:3			6-9	≦45	7-8	260	5	5	5	5	★		☆	★	★	☆	☆	★
酞青蓝 Phthalocyanine Blue BGSW	P.B15:3			6-9	≦45	7-8	260	5	5	5	5			★			★	★	
酞青蓝 Phthalocyanine Blue BGSN	P.B15:3			6-9	≦45	7-8	260	5	5	5	5	★			☆				
酞青蓝 Phthalocyanine Blue BGSP	P.B15:3			6-9	≦45	7-8	280	5	5	5	5					★			★
酞青蓝 Phthalocyanine Blue BGNCF	P.B15:4			6-9	≦45	7-8	260	5	5	5	5	☆	★			★	☆		★
玫瑰色原 Fast Rose Toner	P.V1			6-8	≦55	4	120	3	3	3	2	★							
玫瑰色淀 Fast Rose Lake S	P.V1			6-8	≦55	4	120	3	3	3	2		★						
青莲色原 Fast Violet Toner	P.V3			6-8	≦50	4	120	4	4	4	4	★		☆					
青莲色原 Fast Violet Toner S	P.V3			6-8	≦50	4	120	4	4	4	4		★						
青莲色原 Fast Violet Toner W	P.V3			6-8	≦50	4	120	4	4	4	4	☆		★					★
青莲色淀 Fast Violet Lake	P.V3			6-8	≦50	4	120	4	4	3	3	☆		☆					
永固紫 Permanent Violet 19	P.V19			6-8	≦60	8	300	5	5	5	5	☆	☆	☆	★	★	★	★	★
永固紫 Permanent Violet BL	P.V23			6-8	≦50	8	260	5	5	5	5	★	★	★	★	★	★	★	★
永固紫 Permanent Violet RL	P.V23			6-8	≦50	8	260	5	5	5	5	★	★	★	★	★	★	★	★
酞青绿 Phthalocyanine Green G	P.G7			6-9	≦45	8	240	5	5	5	5	★	★	★	★	★	★	★	★
酞青绿 Phthalocyanine Green GS	P.G7			6-9	≦45	8	240	5	5	5	5	☆	★		★	★			★
酞青绿 Phthalocyanine Green GW	P.G7			6-9	≦45	8	240	5	5	5	5	☆		★			★	★	
酞青绿 Phthalocyanine Green GP	P.G7			6-9	≦45	8	280	5	5	5	5	☆	☆	☆	★	★	☆	☆	★